



code	inside diameter	outside diameter	working pressure	burst pressure	weight nominal	bending radius	length max
	mm inch	mm inch	bar psi	bar psi	kg/m lbs/ft	mm inch	m ft
1457004	102 4	131 5,16	15 225	90 1350	9,39 6,31	1000 39,4	60 200
1452932	152 6	195 7,68	15 225	90 1350	22,12 14,87	1500 59,1	12 40
1456636	203 8	252 9,93	15 225	90 1350	31,62 21,25	2000 78,8	12 40



EN

Asphalt and tar hose, wire reinforced

Standards: EN 13482:2001 Type 2 Class A.

Application: hardwall hose designed for the loading and unloading of hot asphalt and tar, used for dock service.

Not suitable for SubMarine – Offshore Moorings applications.

Temperature: from -15°C (+5°F) to +175°C (+347°F).

Construction

Tube: black, smooth synthetic rubber.

Reinforcement: plies of steel wire cord and embedded steel helix wire.

Cover: black, smooth (wrapped finish), synthetic rubber, weathering, ozone, abrasion, asphalt and oil resistant.

Branding: continuous yellow spiral brand: "IVG - EN 13482:2001 - Type 2 SB/A/I.D. - 15 bar - 175°C - quarter and year of production / ASPHALT and TAR".

CN

沥青管

质量标准: EN 13482:2001 Type 2 Class A.

应用范围: 硬壁管, 设计用于装载和热沥青料, 在码头用于服务不适用于海底 - 海上停泊应用

温度范围: -15°C 至 +175°C

软管结构

内层: 黑, 光滑, 合成橡胶

加强层: 一层钢丝加强, 螺旋钢丝骨架

外层: 黑色光滑 (表面布纹), 耐臭氧、抗恶劣环境、耐磨蚀、耐沥青、耐油的合成橡胶

商标: 橡胶管表面连续螺旋黄色印刷 "IVG - EN 13482:2001 - Type 2 SB/B/I. D. -15 BAR - 175°C - 生产年月ASPHALT and TAR"



Above technical data are referring to applications at room temperature (+20°C).

IVG Colbachini is not liable for the use that differs from what is confirmed in their catalogues, product sheets, offers, order confirmations and contained recommendations. For a correct use refer to "Recommendations for the selection, storage, use and maintenance of rubber hoses" by Assogomma, available on www.ivgspa.it.

With the aim to improve the product, IVG reserves the right to modify the hose specifications without giving any prior notice.

data sheet date/技术参数日期: 10/06/2019

INDICAZIONI DI SICUREZZA PER TUBI ONSHORE BITUMENFLEX

L'impiego ad alta temperatura del tubo BITUMENFLEX è estremamente pericoloso.

Di seguito si forniscono alcune indicazioni di sicurezza per l'uso del tubo ONSHORE BITUMENFLEX, tali indicazioni sono implicitamente presenti nelle normali procedure per l'utilizzo di manichette per il passaggio di bitume caldo:

- **Procedure di utilizzo.**

Si raccomanda siano disponibili adeguate procedure documentate per l'utilizzo di manichette che convogliano bitume.

- **Utilizzo al di sopra di 175 °C?**

I tubi BITUMENFLEX **NON** sono stati progettati per usi al di sopra di +175 °C. Tale temperatura è da intendersi come temperatura massima di utilizzo.

- **Movimentazione.**

I tubi BITUMENFLEX non debbono essere movimentati sollevandoli o agganciandoli direttamente dai raccordi. Si consiglia che, come previsto per manichette che convogliano oli, carburanti e prodotti simili, esse siano curve preferibilmente in mezzeria. Ad alta temperatura la manichetta diventa soffice e deve essere curvata con raggi di curvatura più ampi dei normali raggi di curvatura utilizzati per le manichette idonee al trasferimento di oli e carburanti.

- **Non chiudere la manichetta quando è ancora calda!**

Le manichette non devono essere chiuse/sigillate quando ancora calde. Tale operazione andrà eseguita quando la manichetta è a temperatura ambiente.

- **Indicazioni per la pulizia.**

I raccordi e i tubi ONSHORE BITUMENFLEX **NON** devono essere assolutamente puliti, impiegando per il riscaldamento del bitume raffreddato, fiamme ossidriche o fiamme di alcun genere; se si procede sempre ad un corretto svuotamento della linea, quando il bitume è ancora caldo, non si dovrà procedere ad alcuna particolare pulizia per riutilizzare la manichetta in un secondo tempo. Nell'eventualità che si dovesse procedere necessariamente ad una pulizia interna della manichetta, quando il sistema risulta ancora caldo, è utile impiegare del diesel e una idonea spazzola, pari sistema risulta utile ma più impegnativo in termini di tempo nel caso in cui il bitume si fosse raffreddato.

- **Controlli di sicurezza.**

Particolare attenzione deve essere dedicata ai controlli visivi pre e post utilizzo con cura speciale ai raccordi verificando che siano integri e non presentino situazioni anomale. La copertura non deve mostrare segni di abrasione/lacerazione e non devono essere visibili i tessuti di rinforzo. Tubi schiacciati o che presentino importanti ovalizzazioni devono essere posti fuori servizio.

Si suggerisce che i controlli siano eseguiti da personale specializzato. Le manichette vanno collaudate idraulicamente a temperatura ambiente almeno con frequenza semestrale.

Ogni eventuale anomalia rilevata deve essere registrata e segnalata al responsabile delle operazioni di carico/scarico.

SAFETY HINTS FOR THE USE OF ONSHORE BITUMENFLEX HOSE

The application of BITUMENFLEX hose at high temperature is highly dangerous.

Therefore we supply you some safety hints for the use of ONSHORE BITUMENFLEX hose, these hints must be included in the normal safety procedures for the use of hose assemblies for conveying hot bitumen:

- **Safety Procedures.**

We recommend that appropriate procedures are available for the use of bitumen hose assemblies.

- **Use over 175°C?**

BITUMENFLEX hoses are **NOT** designed for use over +175°C. This temperature must be intended as maximum working temperature.

- **Handling.**

BITUMENFLEX hoses must not be handled by lifting them up or hooking directly from the couplings. We suggest, as expected for hose assemblies that convey oil, fuel and similar products, that they are bent in the middle of the hose. At high temperature the rubber hose gets soft and must be bent with larger bending radius with respect to the standard one for the same hose.

- **Do not close hose assemblies while they are hot!**

Hose assemblies are not to be closed/sealed while still hot. This operation must be done when the hose assemblies are at room temperature.

- **Hints for cleaning.**

The couplings and ONSHORE BITUMENFLEX hoses must **NOT** absolutely be cleaned using blowlamps or flames in general for the warming up of the cooled bitumen. If you always empty the hose line in a correct way, when the bitumen is still hot, it is not necessary to clean the hose in order to re-use the assemblies later. Should the cleaning of the hose assemblies be necessary, when everything is still hot, diesel and a suitable brush can be used: this procedure is efficient but more time-consuming when the bitumen is cold.

- **Safety check.**

Particular attention must be paid to the visual checks before and after use, with specific caution for the couplings: they must be intact and they must not show abnormal signs. The cover must not show abrasions/tears and textile reinforcements must not be visible. Crushed hoses or with big ovalizations must not be used.

We suggest that checks must be done only by specialized staff. Hose assemblies must be tested with a hydraulic system at a room temperature at least every six months.

Each possible defect must be registered and reported to the person in charge of the loading and unloading operations.

SAFETY INFORMATION – USER RESPONSIBILITIES

The service life of rubber hoses mainly depends on the dedicated use. Equipment and systems where the hose is installed must be designed safely. Since our hose can be designed for different applications, IVG Colbachini SpA cannot guarantee the proper functioning of the product for all situations. The analysis of the technical aspects related to specific uses must be performed by the users when choosing the product that meets their requirements. So, in relation to the variety of operating conditions and applications of the IVG hose, the user is solely responsible for the final choice of the product deemed suitable to satisfy the performance and safety requirements called for the application.

The information and technical data shown in the product data sheets must be examined by users with appropriate technical skills.

IVG Colbachini is not responsible for other uses, identified by the end user, that are different from the one shown in its catalogues, product sheets, offers, order confirmations and any recommendations attached.

An inappropriate choice of the product or a failure to follow the procedures of installation, use, maintenance and storage of the hoses may lead to a hose break and cause material damage and/or serious injury to people.

For the selection and proper use of the IVG products you can also refer to the document "Recommendations for selection, storage, use and maintenance of rubber hoses" provided by Assogomma and available on www.ivgspa.it. These recommendations are according to the international standard ISO 8331, "Plastic and rubber hoses and hose assemblies - Guidelines for selection, storage, use and maintenance."

For safety reasons, never exceed the working pressure indicated in the product data sheet.

For specific applications of rubber hoses, please refer to the legal requirements or specific standards; moreover additional recommendations for particularly critical applications are available.

For further information, contact the Marketing department (marketing@ivgspa.it).